



Date of Issue: 11/29/2023 Report Number: 23-003547

Revision Number:1

Date Order Received: 11/21/2023

For the Account of: Teachers Created Resources Inc

12621 Western Ave Garden Grove CA 92841

dentification: Fabric Light Filter
Fier Retardant

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2019 – Test #1

TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	5.1	3.2	37	0.0	0.0
2	5.1	3.6	29	0.0	0.0
3	5.0	2.9	42	0.0	0.0
4	5.0	3.4	32	0.0	0.0
5	5.1	3.2	37	0.0	0.0
6	5.1	2.9	43	0.0	0.0
7	5.1	3.7	27	0.0	0.0
8	5.1	3.2	37	0.0	0.0
9	5.0	3.7	26	0.0	0.0
10	5.0	3.6	28	0.0	0.0
Average	5.1	3.3	34	0.0	0.0

Ammunimata wala	.h4 (am /am .ud), 2 E	Standard Deviation: 6.2	Average 1.2 CD, 52.6
Approximate weig	ht (oz./sq. yd): 2.5	Standard Deviation: 6.2	Average + 3 SD : 52.6
Product Configura	ation: 🗵 Single Laye	r □ Multi Layer	
Conditioning: ☑ Oven at 220°F f		9°F for minimum 30 minutes	☐ 70 ±2°F & 65 ±2%RH for minimum 24 hours
Intended End-use	(if known & other than drapery)): Drapery	
 Where fr seconds Where th Individual Where the 	red to be recorded; however, it is ragments or residues of specime per specimen for the sample of the average weight loss of the 10 all specimens will be listed as a fame specimens do not demonstrate.	10 specimens, the material shall be specimens in a sample is greater tha ailure if it exceeds mean + 3 SD	mber continue to burn for more than an average of 2
CONCLUSION	Based on the above Results an ⊠ Complies ☐ Does Not Comply	nd Acceptance Criteria, the item test	ed:
	certify that the above results wer andard stated above.	re obtained after testing specimen in	accordance with the procedures and equipment

553 76th Street, Byron Center, MI 49315

Authorized Signature

P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1

Date Order Completed: 11/27/2023